



# ALCANTARA COVER SPECIFICATIONS

			5205	5267	
Composition	Alcantara	Polyester	68	68	%
		Polyurethane	32	32	%
Backing	Polyester Cotton		65	65	%
			35	35	%
	FR/Alcantara			25	%
Thickness			≥ 0.95	≥ 0.95	mm
Unit weight		UNI EN 29073-1	≥ 325	≥ 400	g/m <sup>2</sup>
Width			≥ 142	≥ 142	cm
Breaking load	Lengthwise Transversal	UNI EN 29073-3	≥ 700	≥ 700	N
		UNI EN 29073-3	≥ 400	≥ 400	N
Wear resistance	Martindale	UNI EN ISO 12947-1/2/3/4	≥ 30,000 ≥ 150,000	≥ 30,000 ≥ 150,000	cycles <sup>+</sup> cycles <sup>**</sup>
Colour fastness					
To light	Xenotest beta	VDA 75202 (2 FAKRA)	≥ 3	≥ 3	grey scale
To rubbing	Dry Wet	UNI EN ISO 105-X12	≥ 4	≥ 4	white scale
		UNI EN ISO 105-X12	≥ 3/4	≥ 3/4	white scale
Cohesion		UNI EN ISO 2411	≥ 10	≥ 10	N
FR version	Fire resistance	FMVSS 302		< 100	mm/min

\* No significant change in surface appearance

\*\* End point

Alcantara Pannel is also available in the version Flame Retardant (FR), compliant with the directive 95/28 CE.

FR Product code: 5257

**Email** | [sales@ukhide.co.uk](mailto:sales@ukhide.co.uk)

**Phone** | +44 (0)1932 353 338

Visit us online at

[www.ukhide.co.uk](http://www.ukhide.co.uk)