



ALCANTARA PANNEL SPECIFICATIONS

			5012	5056	
Composition	Alcantara	Polyester	68	68	%
		Polyurethane	32	32	%
	FR contnet/Alcantara			25	%
Thickness			0.83	0.85	mm
Unit weight		UNI EN 29073-1	230	285	g/m ²
Width			≥ 142	≥ 142	cm
Breaking load	Lengthwise Transversal	UNI EN 29073-3 UNI EN 29073-3	≥ 220 ≥ 170	≥ 220 ≥ 170	N N
Wear resistance	Martindale	UNI EN ISO 12947-1/2/3/4	≥ 30,000 ≥ 150,000	≥ 30,000 ≥ 150,000	cycles* cycles**
Colour Fastness					
To light	Xenotest Beta	VDA 75202 (2 FAKRA)	≥ 3	≥ 3	grey scale
To rubbing	Dry Wet	UNI EN ISO 105-X12 UNI EN ISO 105-X12	≥ 4 ≥ 3/4	≥ 4 ≥ 3/4	white scale white scale
FR version	Fire resistance	FMVSS 302		< 100	mm/min
Standard	1.0 - 1.2	750	Half hide		
Standard Club	1.4 - 1.6	1000	Half hide		

* No significant change in surface appearance

** End point

Alcantara Pannel is also available in the version Flame Retardant (FR), compliant with the directive 95/28 CE.

FR Product code: 5256

Email | sales@ukhide.co.uk

Phone | +44 (0)1932 353 338

Visit us online at

www.ukhide.co.uk