



TEST	TEST METHOD	SPECIFICATION	RESULT
Tensile Strength	BS 3144	8.0 N/mm <sup>2</sup> in any direction	
Elongation @ Break	BS 3144	25/60%	
Tear Force Stitch Tear	BS 3144 Baumann BS 1309	40 N/mm	
<i>Flex Cracking</i> Original Sample After Heat Ageing (70 days @ 80°C)	JNS 30, 32, 10 / BS 3424 pt 14 PT9 : Mtd 11	100,000 cycles min / no cracking 10,000 cycles min / no cracking	
Resistance to Perspiration	BS 1006 E04	GS 4/5 Alkali Acid	Grain Flesh
<i>Colourfastness to Rubbing</i> Wet Dry Cleaner	BS 3424 PT 14 Mtd 16 BS 3424 PT 14 Mtd 16 JNS 30, 11, 06	GS 4/5 GS 4/5 GS 4/5	
Weight Per Unit Area	BS 3424 : Pt 3 Method 5a	780 gr/m <sup>2</sup> +/- 10%	
Flammability	JNS 30, 45, 05 FMV SS 302	100 mm/min max	
Thickness	BS 3144	1.0/1.4	
Odour	JNS 30, 47, 01	Free from offensive odour	
Chrome Content	SLTC 8	3.5/4.2%	
Water Permeability	SLTC 25 - IUP/14		
Sweat Resistance	BS 1006/E04	GS 4/5 min	
Rubfastness - VESLIC	SLF 450 - (IUF 450) DRY 2000 WET 500 PETROL 10 ALCOHOL 10	GS 5 min GS 4/5 min GS 4 min GS 4 min	
Colour Migration	Crock BS 3424	Grain GS 4/5 Flesh GS 3/4	

## What you should know about ordering leather

Due to the beautiful natural characteristics of leather, there may be some variation in shade and texture within a hide, and between hides. Although hides are free from excessive scars, there is always some evidence of their natural origin. Size will also vary between hides, but a typical hide is between 4.5-5.5m<sup>2</sup>. Please contact us for sizes available.

Samples are a good guide to colour and finish, but you should bear in mind an exact match cannot be guaranteed.

**Email** | [sales@ukhide.co.uk](mailto:sales@ukhide.co.uk)

**Phone** | +44 (0)1932 353 338

Visit us online at

[www.ukhide.co.uk](http://www.ukhide.co.uk)

