



TEST	TEST METHOD	ACTUAL VALUES
Strength	DIN 53326	1.0mm - 1.4mm
Tanning		Synthetic, vegetable. Free of chrome
Mass per unit area	DIN 53326	620 - 980 g/sqm
Tension test Tensile test Breaking elongation	DIN 53328 Specimen 2 Specimen 2	> 120 N 35 - 70%
Tear Strength	DIN 53329/A DIN 53329/B	> 25 N > 20 N
Behaviour after 20,000 folds	DIN 53351	No cracks at 6 times magnifying
Behaviour after 10,000 folds after ageing		No cracks at 6 times magnifying
Water vapour permeability	DIN 53333	1.0 mg/sqcm
Fastness to Rubbing Dry Wet Wet after storage in water	DIN 53339 Evaluation DIN 54002	4 - 5 class 4 - 5 class 4 - 5 class
Sweat		4 - 5 class
Top coat adhesion		3.5 N/cm
Fastness to UV	DIN 75202	5 - 7 class blue scale
Flammability	FMVSS 302	< 100 mm/min
Odour test VDA list	VDA 270 C3	< 3 class Keeping to the list

What you should know about ordering leather

Due to the beautiful natural characteristics of leather, there may be some variation in shade and texture within a hide, and between hides. Although hides are free from excessive scars, there is always some evidence of their natural origin. Size will also vary between hides, but a typical hide is between 4.5-5.5m². Please contact us for sizes available.

Samples are a good guide to colour and finish, but you should bear in mind an exact match cannot be guaranteed.

Email | sales@ukhide.co.uk

Phone | +44 (0)1932 353 338

Visit us online at

www.ukhide.co.uk

