



THRUXTON SPECIFICATIONS

TEST	TEST METHOD	MEASUREMENT UNIT	RESULT
Tensile strength	ISO 3376	N	≥ 130
Adhesive strength of finish	ISO 11644	N/cm	≥ 4
Tear propagation force Stitch tear resistance	ISO 3377 - 1 ISO 23910	N	≥ 20 ≥ 50
Behaviour at permanent folding	UNI - ISO 5402	50,000 cycles	No damage on visual evaluation
Colour fastness to light - 72 hours	ISO 105 B06	Grey scale	≥ 4
<i>Colour fastness to Rubbing</i> Wet - 500 cycles Dry - 1500 cycles Sweat - 80 cycles	UNI ENO ISO 11640 & ISO 105-A02 UNI ENO ISO 11640 & ISO 105-A02 UNI ENO ISO 11640 & ISO 105-A02 & ISO 105-E042	Grey scale Grey scale Grey scale	500/ ≥ 4 1500/ ≥ 4 80/ ≥ 4
pH Value	ISO 4045		≥ 3.5
Difference figure - only for pH < 4 or > 10	ISO 4045		≤ 0.7
Thickness	ISO 2589	1.0 - 1.2mm	
Flammability	FMVSS 302	mm/min	< 100
Ageing	4h at 70°C	Visual evaluation	min 4

What you should know about ordering leather

Due to the beautiful natural characteristics of leather, there may be some variation in shade and texture within a hide, and between hides. Although hides are free from excessive scars, there is always some evidence of their natural origin. Size will also vary between hides, but a typical hide is between 4.5-5.0m². Please contact us for sizes available.

Samples are a good guide to colour and finish, but you should bear in mind an exact match cannot be guaranteed.

Email | sales@ukhide.co.uk

Phone | +44 (0)1932 353 338

Visit us online at

www.ukhide.co.uk

