



AUTOMOTIVE FULL GRAIN NAPPA

CHARACTERISTIC	UNIT	REQUIREMENT	TEST METHOD
Thickness	mm	1.0 - 1.4	DIN 53326
Mass per unit area	g/qm	620 - 980	DIN 53327
Tension test Tensile test Breaking elongation	N %	> 120 35 - 70	DIN 53328 Specimen 2 Specimen 2
Tear strength	N	> 25 > 20	DIN 53329/A DIN 53329/B
Behaviour after 20,000 folds		No cracks at 6 times magnifying	DIN 53351
Behaviour after ageing 1 period 10,000 folds		No cracks at 6 times magnifying	
Water vapour permeability	mg/qcm	1.0	DIN 53333
Rub fastness Dry Wet Wet after storage in water	Class Class Class	4 - 5 4 - 5 4 - 5	DIN 53339 evaluation DIN 54002
Sweat	Class	4 - 5	
Top coat adhesion	N/cm	3.5	
High temperature light exposure	Class blue scale	5.7	DIN 75202
Flammability	mm/min	< 100	FMVSS 302
Odour test	Class	< 3	VDA 270 C3
VDA list		Keeping to the list	

What you should know about ordering leather

Due to the beautiful natural characteristics of leather, there may be some variation in shade and texture within a hide, and between hides. Although hides are free from excessive scars, there is always some evidence of their natural origin. Size will also vary between hides, but a typical hide is between 4.5-5.5m². Please contact us for sizes available.

Samples are a good guide to colour and finish, but you should bear in mind an exact match cannot be guaranteed.

Email | sales@ukhide.co.uk

Phone | +44 (0)1932 353 338

Visit us online at

www.ukhide.co.uk

