



PRIMA FAUX LEATHER

CHARACTERISTIC	TEST METHOD	VALUES
Strength	DIN EN ISO 2286-3	1.3mm \pm 0.1mm
Mass per unit area	DIN EN ISO 2286-2	740 \pm 50 g/qm
Tear strength Length Across	DIN 53356	\geq 30 N \geq 30 N
Behaviour after folding length Across	DIN 53359 DIN 55014-23/50-2	\geq 50,000 folds \geq 50,000 folds
Tensile strength Length Across	DIN 53354	\geq 400 N \geq 200 N
Elongation length Across	DIN 53354	\geq 80% \geq 180%
Stitch burst strength Length Across	DIN 53506	\geq 50 N \geq 40 N
Adhesion length Across	DIN 53357	\geq 30 N \geq 30 N
Light fastness	DIN EN ISO 105-B02	\geq 6 degree
Water resistance	DIN EN 20811	\geq 200 cm WS
Low temperature resistance	DIN 53361	- 20 °C
Flammability	DIN 75200 / ISO 3795 / MVSS 302	\leq 100 mm/min

What you should know about ordering faux leather

Fabric width is 140cm. Roll length is 30 linear metres.

Samples are a good guide to colour and finish, but you should bear in mind an exact match cannot be guaranteed.

Email | sales@ukhide.co.uk

Phone | +44 (0)1932 353 338

Visit us online at

www.ukhide.co.uk