



DINAMICA TECHNICAL SPECIFICATIONS

TEST	TEST METHOD	VALUES
Thickness	ISO 5084	1.10 mm (\pm 0.10)
Weight	ISO 29073/1	300 g/m ² (\pm 30)
Width	UNI EN 1773	\geq 140 cm
Tensile strength	ISO 13934/1	\geq 500 N (Auto) \geq 400 N (Stretch)
Tear strength	ISO 13937/2	\geq 15 N
Abrasion resistance	with Martindale ISO 12947	50,000 Cycle (Auto) 35,000 Cycles (Stretch)
Colour fastness to light	\geq Grey Scale ISO 105-A02 ISO 105-B06	3 Exposure Cycles
Resistance to rubbing	Grey Scale - ISO 105-A03	\geq 4 (Wet/Dry) \geq 3 (Wet) Dark Colours
Retardant specification	FMW SS 302	\leq 100 mm/min
Colour tolerance versus master sample	\geq Grey Scale ISO 105-A02	

Dinamica is a piece-dyed microfibre. Colours can slightly change from batch to batch.

Colour swatch cards, samples and colours shown on our website are purely representative.

Email | sales@ukhide.co.uk

Phone | +44 (0)1932 353 338

Visit us online at

www.ukhide.co.uk