



TEST	TEST METHOD	SPECIFICATION
Tensile Strength	BS 3144	8.0 N/mm ²
Tear Force Stitch Tear	BS 3144 Baumann BS 1309	40 N/mm
Abrasion Taber	JNS 30,04,05	1500 cycles CS 10, 500g No penetration of coated surface of leather
Flex Cracking	JNS 30,32,10 BS 3424 Pt 14	100,000 cycles min / no cracking
After Heat Ageing 7 days @ 80 C	Pt 9: Mtd 11	100,000 cycles min / no cracking
Light fastness	JNS 30,11, 02	4/5
Thickness	BS 3144	1.2 +- 0.2mm
Rubfastness VESLIC	Dry 2000 Wet 500 Petrol 10 Alcohol 10	GS 5 min GS 4/5 min GS 4 min GS 4 min
Flammability	JNS 30 45 05 FMV SS 302	100mm min/max

If you have additional flammability requirements such as FAR 25 and CRIB 5, please contact us to discuss.

Our samples should be viewed as a guide to texture and finish in this respect, and we recommend that hides, when delivered, should be viewed prior to marking or cutting as no returns can be accepted unless the hides are in their original condition.

Connolly is the registered trademark of Connolly Retail Limited and is used under license.

Email | sales@ukhide.co.uk

Phone | +44 (0)1932 353 338

Visit us online at

www.ukhide.co.uk