



TEST	TEST METHOD	MEASUREMENT UNIT	RESULT
Flexing Endurance - Dry 50,000 cycles	UNI EN ISO 5402		No damage
Tear Strength - Single edge tear	UNI EN ISO 3377 - 1N		> = 20
Burning behaviour to cigarette and match flame	BS 5852:1979, source 0-1 BS EN 1021-1-2 : 2006		Pass
Colour fastness to artificial light - exposition energy 16,000 kj/m ²	UNI EN ISO 105 B02 (MET.5)	Blue scale	> = 3
Colour fastness to Rubbing Wet - 20 cycles Dry - 50 cycles Sweat - 20 cycles	UNI ENO ISO 11640 :1998 11641 pH8	Grey scale	> = 3 > = 3 > = 2

Bovine of European origin, lightly buffed natural grain. Finished thickness 0.8-1.0mm. Average leather size 4.8-5.0 sqm. Chrome tanning, aniline dyed.

Water based finish, with waxes, anilines and resins finely dispersed for a distressed appearance. Stiff handle, slippery feel and semi-gloss appearance. Being an aniline product, some colour variation between different hides and batches is to be expected.

What you should know about ordering leather

Due to the beautiful natural characteristics of leather, there may be some variation in shade and texture within a hide, and between hides. Although hides are free from excessive scars, there is always some evidence of their natural origin. Size will also vary between hides, but a typical hide is between 4.8-5.0m². Please contact us for sizes available.

Samples are a good guide to colour and finish, but you should bear in mind an exact match cannot be guaranteed.

Email | sales@ukhide.co.uk

Phone | +44 (0)1932 353 338

Visit us online at

www.ukhide.co.uk

