



WINCHESTER SPECIFICATIONS

TEST	TEST METHOD	MEASUREMENT UNIT	RESULT
Flexing Endurance - Dry 50,000 cycles	UNI EN ISO 5402		No damage
Tear Strength - Single edge tear	UNI EN ISO 3377 - 1	N	> = 20
Smoulder resistance, cigarette and match flame	CAL TB-117 (2013, Sec 1) BS 5852:1979, source 0-1 BS EN 1021-1-2 : 2006		Pass
Colour fastness to artificial light - exposition energy 16,000 kj/m ²	UNI EN ISO 105 B02 (MET.5)	Blue scale	> = 2
<i>Colour fastness to Rubbing</i> Wet - 20 cycles Dry - 50 cycles Sweat - 20 cycles	UNI ENO ISO 11640 :1998 ISO 11641 pH8	Grey scale	> = 3 > = 3/4 > = 3

Full grain bovine of European origin with a finished thickness 0.9-1.1mm. Average leather size approximately 4.8 - 5.0 sqm. Chrome tanning.

Aniline dyed, finished with oils - natural waxes and resins. Leather has a firm, waxy feel and a shiny appearance with a light two-tone effect. Being an aniline product, some colour variation between different hides and batches is to be expected.

What you should know about ordering leather

Due to the beautiful natural characteristics of leather, there may be some variation in shade and texture within a hide, and between hides. Although hides are free from excessive scars, there is always some evidence of their natural origin. Size will also vary between hides, but a typical hide is between 4.8-5.0m². Please contact us for sizes available.

Samples are a good guide to colour and finish, but you should bear in mind an exact match cannot be guaranteed.

Email | sales@ukhide.co.uk

Phone | +44 (0)1932 353 338

Visit us online at

www.ukhide.co.uk

