



CAMBRIDGE SPECIFICATIONS

| TEST | TEST METHOD | MEASUREMENT UNIT | RESULT |
|--|---|------------------|-----------|
| Flexing Endurance - Dry 50,000 cycles | UNI EN ISO 5402 | | No damage |
| Tear Strength - Single edge tear | UNI EN ISO 3377 - 1 | N | > = 20 |
| Smoulder resistance, cigarette and match flame | BS 5852:1979, source 0-1 BS EN 1021-1-2 : 2006 | | Pass |
| Colour fastness to artificial light - exposition energy 16,000 kj/m ² | UNI EN ISO 105 B02 (MET.5) | Blue scale | > = 2 |
| Colour fastness to Rubbing Dry - 50 cycles | UNI ENO ISO 11640 :1998 | Grey scale | > = 3 |

Full grain bovine leather sourced from European cattle with smooth surface. Average hide size is approximately 5 sqm and thickness of 1.2-1.4mm. Chrome tanned.

Pure aniline finished with natural oils and waxes added in the dye drum to give the leather a beautiful transparent vegetal tanning look with a slight pull up effect. As a natural leather product, some imperfections in the hides and colour variation between different hides and batches is to be expected.

What you should know about ordering leather

Due to the beautiful natural characteristics of leather, there may be some variation in shade and texture within a hide, and between hides. Although hides are free from excessive scars, there is always some evidence of their natural origin. Size will also vary between hides, but a typical hide is between 4.8-5m². Please contact us for sizes available.

Samples are a good guide to colour and finish, but you should bear in mind an exact match cannot be guaranteed.

Email | sales@ukhide.co.uk

Phone | +44 (0)1932 353 338

Visit us online at

www.ukhide.co.uk

