



# KENSINGTON SPECIFICATIONS

TEST	TEST METHOD	MEASUREMENT UNIT	RESULT
Flexing Endurance - Dry 50,000 cycles	UNI EN ISO 5402		No damage
Tear Strength - Single edge tear	UNI EN ISO 3377 - 1	N	> = 20
Smoulder resistance, cigarette and match flame	CAL TB-117 (2013, Sec 1) BS 5852:1979, source 0-1 BS EN 1021-1-2 : 2006		Pass
Colour fastness to artificial light - exposition energy 16,000 kj/m <sup>2</sup>	UNI EN ISO 105 B02 (MET.5)	Blue scale	> = 3
<i>Colour fastness to Rubbing</i> Wet - 20 cycles Dry - 50 cycles Sweat - 20 cycles	UNI ENO ISO 11640 :1998 ISO 11641 pH8	Grey scale	> = 3 > = 3 > = 3

Bovine leather sourced from European cattle with smooth appearance, aniline finished using oils and waxes. Average hide size 4.5-4.8 sqm and thickness of 0.9-1.1mm. Chrome tanned.

Aniline dyed, finished with high quality oils. Soft leather with a slight two-tone effect. Being an aniline product, some colour variation between different hides and batches is to be expected.

## What you should know about ordering leather

Due to the beautiful natural characteristics of leather, there may be some variation in shade and texture within a hide, and between hides. Although hides are free from excessive scars, there is always some evidence of their natural origin. Size will also vary between hides, but a typical hide is between 4.5-4.8m<sup>2</sup>. Please contact us for sizes available.

Samples are a good guide to colour and finish, but you should bear in mind an exact match cannot be guaranteed.

**Email** | [sales@ukhide.co.uk](mailto:sales@ukhide.co.uk)

**Phone** | +44 (0)1932 353 338

Visit us online at

[www.ukhide.co.uk](http://www.ukhide.co.uk)

